

Eppendorf Certificate

Certificate of Quality

Eppendorf Tubes® – Typical values of trace metal release

The values in the table indicate typical values of trace metal concentrations obtained by incubating Eppendorf Tubes with concentrated nitric acid for 1 hour (see Materials and Methods, page 2).

As the indicated values were determined in a one-time measurement, they cannot be guaranteed for every lot of Eppendorf Tubes. Rather, they provide an indication of the extent trace elements can be eluted from Eppendorf Tubes.

	Trace metal release [ng/μL]								
	Al	Cd	Cr	Cu	Hg	Mn	Ni	Pb	Zn
Eppendorf Safe-Lock Tubes									
0.5 mL	0.003	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
1.5 mL	0.002	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
2.0 mL	0.002	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
Eppendorf Tubes Protein LoBind									
0.5 mL	0.006	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
1.5 mL	0.004	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
2.0 mL	0.004	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
5.0 mL	< 0.001	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
Eppendorf Tubes DNA LoBind									
0.5 mL	0.004	< 0.00002	0.0001	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
1.5 mL	0.003	< 0.00002	0.0001	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
2.0 mL	0.003	< 0.00002	0.0001	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
5.0 mL	< 0.001	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
Eppendorf Tubes 5.0 mL									
5.0 mL	< 0.001	< 0.00002	< 0.00005	< 0.0001	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
5.0 mL with screw cap	< 0.001	< 0.00002	< 0.00005	0.000183	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
Eppendorf Conical Tubes									
15 mL	< 0.001	< 0.00002	< 0.00005	0.00016	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001
50 mL	< 0.001	< 0.00002	< 0.00005	0.000086	< 0.001	< 0.00005	< 0.00005	< 0.00005	< 0.001

Eppendorf Certificate

Materials and Methods

Eppendorf Tubes were filled to their nominal volume with concentrated nitric acid (65 %) and incubated for 1 hour at room temperature. The eluate was then analyzed by inductively coupled plasma mass spectrometry (ICP-MS). The trace metal concentrations are stated in ng/ μ L.

The values represent an average of three individually analyzed samples. All values labeled with "<" indicate concentrations below the detection limit of the ICP-MS method. The other trace metal release values were calculated from their surface/volume ratio of the tube.

No metal release was observed after 5 to 10 times rinsing with concentrated nitric acid or after rinsing with 10 % acetic acid or water. All analyses were performed by an independent laboratory accredited according to DIN ISO/EC 17025.

June 2016

Page 2 of 2

0012 602.500-01



Daniel Voss
Product Line Manager
Consumables



Dr. Birgit Schreiber
Vice President Quality Management &
Regulatory Affairs

Your local distributor: www.eppendorf.com/contact
Eppendorf AG · 22331 Hamburg · Germany
E-mail: eppendorf@eppendorf.com

ISO 9001
Certified

ISO
13485
Certified

ISO
14001
Certified

Eppendorf®, the Eppendorf logo and Eppendorf Tubes® are registered trademarks of Eppendorf AG, Germany.
All rights reserved, incl. graphics and pictures. Copyright 2016 © by Eppendorf AG.